



## Technical Data for Duron Timber Floor Finish Gloss

### Product Type

Aromatic moisture curing clear polyurethane

### Properties

An extremely tough but flexible, clear, chemical, stain and wear-resistant coating.

### Principal uses

This coating is designed for use as an economical wear resistant binder and finish coating for internal timber and seamless flooring, and as a chemical, stain and wear-resistant sealer/finish for (freshly ground) internal concrete and masonry.

### Typical properties

Solids:	45%
Specular Gloss 60° :	93
Coverage:	6-8 metres/litre/coat
Drying time:	2.5 hrs, (25°C, 65% Rel. Hum)
Recoat Window:	4-24 hrs
Viscosity:	90 cPs approx. (30°C)
Durability:	NOT Suitable for exterior exposure (will yellow slowly with age and UV exposure)
Water Resistance:	Excellent (no effect after 7 days immersion)
Chemical resistance:	Good resistance to acids, alkalis and most common solvents including: alcohols, aromatic hydrocarbons, brake fluid, diesel and machine oil.
Stain resistance:	Excellent
Abrasion Resistance:	Excellent- weight loss of 20 mg for 1 kg weight on CS10 Calibrase wheel, 1500 cycles (Taber).
Monomeric isocyanate:	<0.7%
Ancillaries available:	Wet Edge Extender, PU Cleaning Solvent, PU Thinners

### Packaging

20 Litre cans with polypress spout.

---

All information is given in good faith without warranty. This information does not constitute a specification.

Users are encouraged to assess the product under their own conditions and for their own applications.